



EUROPEAN  
COMMISSION

Brussels, **XXX**  
[...](2016) **XXX** draft

ANNEX 1

## **ANNEX**

**to the**

**Commission Delegated Regulation**

**of xx**

**on the conditions for classification, without testing, of external renders and internal  
plasters based on organic binders covered by the harmonised standard EN 15824 and  
rendering and plastering mortars covered by the harmonised standard EN 998-1 with  
regard to their reaction to fire**

## ANNEX

<b>Products<sup>1</sup></b>	<b>Maximum organic content<sup>2</sup> (% in weight)</b>	<b>Maximum mass per unit area<sup>3</sup> (kg/m<sup>2</sup>)</b>	<b>Class<sup>4</sup></b>
External renders and internal plasters based on organic binders covered by the harmonised standard EN 15824	<b>≤ 9,0</b>	<b>≤ 4,0</b>	<b>B - s2, d0</b>
External renders and internal plasters based on organic binders covered by the harmonised standard EN 15824 and Rendering and plastering mortars covered by the harmonised standard EN 998-1	<b>≤ 2,5</b>	<b>≤ 6,0</b>	<b>A2 - s1, d0</b>
	<b>≤ 4,0</b>	<b>≤ 4,0</b>	
	<b>≤ 5,0</b>	<b>≤ 2,0</b>	

<sup>1</sup> Products delivered in paste or in powder form and used for external and internal covering on walls, columns, partitions, and ceilings. The performance of substrates shall be at least class A2 - s1, d0 and the density shall not be less than 525 kg/m<sup>3</sup>.

<sup>2</sup> Related to the solids content (comparable to the fully dried plaster/render as applied to the substrate).

<sup>3</sup> Related to the wet product (ready to use state).

<sup>4</sup> Class as set out in Table 1 of the Annex to Delegated Regulation (EU) 2016/364.